



WAREHOUSE MATRIX

A.B.N 29 764 742 043

PO Box 24
Balaklava SA 5461

Telephone 08 8862 2078
Facsimile 08 8862 2033

TECHNICAL INFORMATION

SEALED TIMBER FLOOR STRIPPING PROCEDURE

For the **removal** of old, discoloured, built up wax or metal cross-linked polishes or sealer finishes from sealed timber or parquet flooring.

EQUIPMENT

Wet Floor sign.

Old mop and plastic bucket for floor stripping solution

Clean mop and roller bucket for rinse water

Wet pick-up vacuum, (additional roller buckets and mops will be required if wet vacuum is not available)

16" Slow speed polishing machine fitted with Instaloc or Velcro drive disk

16" Bassine brush, black stripping or super strip pad

Edge pad holder and brown strip pad

Hand and feet protection

METHOD - ENSURE ADEQUATE VENTILATION

PROTECT CARPET AREAS AROUND FLOOR FROM MACHINE SPRAY

1. Apply recommended All Purpose Floor Strip Emulsion, either neat or at the recommended dilution rate to a workable area of the floor surface to be stripped using an old cotton or poly cotton mop.
2. Allow approximately 5 - 10 minutes contact time to ensure complete emulsification of old finish.
3. Scrub the area with the 16" slow speed polisher equipped with either a bassine brush, black or super strip pad.

DO NOT ALLOW AREA BEING STRIPPED TO DRY

4. Scrub around floor edges where machine cannot reach with pad holder and pad.
5. Pick up slurry with wet pick-up vacuum, or mops and buckets.
6. Rinse stripped area of floor surface with clean mop and water, ensuring that no residue of the old finish is left in contact with the floor surface.
7. When clean and dry, floor is ready for resealing.

